

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 62-088134

(43)Date of publication of application : 22.04.1987

(51)Int.Cl.

G11B 5/702
G11B 5/708

(21)Application number : 60-227650

(71)Applicant : SONY CORP

(22)Date of filing : 15.10.1985

(72)Inventor : IKUYAMA SEIICHI
MIYAZAKI TAKAHIRO
YATAGAI HIROSHI

(54) MAGNETIC RECORDING MEDIUM

(57)Abstract:

PURPOSE: To improve the dispersibility of magnetic powder and the surface characteristic of a magnetic layer and to obtain a magnetic recording medium having excellent durability and runnability and good magnetic characteristic and electromagnetic conversion characteristic by incorporating a specific polyurethane resin as a binder into the magnetic layer essentially consisting of ferromagnetic powder and binder.

CONSTITUTION: The polyurethane resin having a siloxane bond in the molecular chain and having at least one kind among a -SOdM group, -OSO3M group, -COOM group, -P(=O, side chain) (OM') group is used as the binder of the magnetic layer which consists essentially of the ferromagnetic powder and binder and is formed on a nonmagnetic base. M is hydrogen or alkali metal, M' is hydrogen, alkali metal or hydrocarbon group. The atm. of the polar group to be introduced into the polyurethane resin is preferably 0.01W1.0mmol/g and the concn. of the siloxane group is preferably 0.03W3mmol/g. The number average mol.wt. of the polyurethane resin is preferably 104W105.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or

application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office